

# Technical Information

## 40-510








Ambient clear

VOC Ambient clear for baslac basecoat

- Easy and safe to spray, fast drying, easy to polish
- To be used for airdry
- Simple mixing ratio

### Application

	<b>Mixing Ratio</b>	100 % by volume	40-510
	<b>4:1</b>	25 % by volume	50-510
	<b>Spray viscosity at 20°C</b>	DIN 4: 20 s	
	<b>Potlife at 20°C</b>	25 min	
	<b>HVLP spray gun</b>		
	Nozzle size	1.3 mm	
	Application pressure	2 bar	
	Nozzle pressure	0.7 bar	
	<b>Compliant gravity-feed spray gun</b>		
	Nozzle Size	1.3-1.4 mm	
	Application Pressure	2 bar	
	<b>Number of spraycoats</b>	1	
	<b>Film thickness</b>	40 µm	
	<b>Application Remark</b>	alternativ: 2 spray coats: 50 - 60µm	

#### Safety advice:

**2004/42/IIIB(d)(420)419:** The EU limit value for this product ( product category: IIB.d) in ready to use form is max 420 g/l of VOC. The VOC content of this product is 419 g/l.

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



# Technical Information

## 40-510



Ambient clear

### Drying

	<b>Drying at 20 °C</b>	1 h dust-free: 15 min. polishable: 1 ½ h
	<b>Drying at 60 °C</b>	5 min polishable: after cool down
	<b>Infrared (short wave)</b>	5 min
	<b>Infrared (medium wave)</b>	5-10 min



#### Safety advice:

**2004/42/IIIB(d)(420)419:** The EU limit value for this product ( product category: IIB.d) in ready to use form is max 420 g/l of VOC. The VOC content of this product is 419 g/l.

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.